

Test Report

No: TX50972 /2011 /SH

Date: May 30, 2011

Page: 1 OF 2

Makalot Ind. Co., Ltd.
3F., No. 106-2, Sec. 2, Chung Shan N. Road,
Taipei, Taiwan

The following samples were submitted and identified by the client as:

Sample Description : Two samples of knitted fabrics heat up in (A) burgundy and (B) grey str

Fiber Content : 58% Acrylic 37% Tencel 5% Spandex

Fabric Weight : 200gm²

Construction : 30S/1

End Use : Garment

Buyer : Lativ

Country of Origin : Taiwan


Sample Receiving Date : May 13, 2011

Test Performance Period : May 13 to May 30, 2011

Test Performed : Selected test(s) as requested by applicant.

Test Results : For further details, please refer to the following page(s).

Signed for and on behalf of
SGS Taiwan Ltd.



Cheng Yueh-Er, Ellen
Supervisor

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested. This test report cannot be reproduced, except in full, without prior written permission of the Company. 除非另有說明，此報告結果僅對測試之樣品負責。本報告未經本公司書面許可，不可部份複製。

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at www.sgs.com/terms_and_conditions.htm and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at www.sgs.com/terms_e-document.htm. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

Test Results:


Test item: Temperature survey

Test method:

Put the test sample (20cm x 20cm) into a drying machine for 4 hours. Then place the sample into a desiccator that has silica gel inside, and leave it overnight. Fold the testing sample in half, put the temperature sensor on the center surface, and then again fold it half. Place the sample into an environment of 20°C & 40%RH for 2 hours, and then change to 20°C & 90%RH environment. Measure the result every minute for 15 minutes timeframe.

Time (min)	Temperature(°C)	
	(A)	(B)
0	20.1	20.1
1	21.1	21.1
2	23.0	22.8
3	24.3	24.0
4	24.7	24.5
5	24.5	24.5
6	24.2	24.1
7	23.8	23.6
8	23.2	23.1
9	22.6	22.6
10	22.1	22.0
11	21.7	21.7
12	21.6	21.6
13	21.7	21.6
14	21.7	21.7
15	21.6	21.6

Tested by other laboratory



*** End of Report ***

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested. This test report cannot be reproduced, except in full, without prior written permission of the Company. 除非另有說明，此報告結果僅對測試之樣品負責。本報告未經本公司書面許可，不可部份複製。

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at www.sgs.com/terms_and_conditions.htm and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at www.sgs.com/terms_e-document.htm. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.